

# Indeko-plus

A class of its own, extremely yielding and economic.  
Emission-minimised, unplasticized and solvent-free.



## Product Description

### Field of Application

Top-quality coating for all internal walls and ceilings. Indeko-plus has double covering power, hence in most cases one evenly applied coat is sufficient. The product dries very fast without emitting any offensive odour and is therefore particularly suitable when time is pressing and occupants or users are not to be incommoded by the smell of fresh paint, e.g. painting or redecoration in hospitals, nursing homes, warehouses, hotels, restaurants, offices, schools, playschools, surgeries, public buildings and private living quarters.

### Material Properties

- Water-thinnable, ecologically compatible, low odour.
- Free of fogging-active substances.
- Easy to touch up.
- Double covering power.
- High degree of whiteness.
- Slightly filling, non-yellowing.
- Diffusion-capable, sd-value < 0.1 m

### Material Base / Vehicle

Synthetic resin dispersion/emulsion according to German standard DIN 55945.

### Packaging/Package Size

- **Standard Product:** 5 litres and 12.5 litres
- **ColorExpress:** 1.25 l, 2.5 l, 5 l, 7.5 l and 12.5 litres

### Colours

White.

Indeko-plus is tintable with CaparolColor or AVA colourants. If more than one bucket is manually tinted, all product must be thoroughly mixed before use in order to avoid colour differences. Quantities of 100 litres or more in individual colour shades may be ordered ready tinted ex factory. Indeko-plus (Base 1-3) can be tinted via the ColorExpress tinting machine system according to all current colour collections. Check tinted product prior to the application to avoid colour differences. Always use paint of same batch, when applying on seamless surfaces. Brilliant, intensive colour shades can have a lower opacity (hiding/covering power). It is therefore advisable to apply a first coat in a similar hiding pastel tint, based on white. Possibly a second finishing coat may be necessary.

### Gloss Level

Dead-matt (according to DIN EN 13 300)

### Storage

Keep in a cool, but frost-free place.



## Technical Data

**Characteristics according to DIN EN 13 300:** Tinting may cause variations.

- Wet abrasion: Class 1, corresponds to "scrub resistant" according to German standard DIN 53778
- Contrast ratio: Opacity/covering power class 1, with a spreading rate of 8 m<sup>2</sup>/l or 125 ml/m<sup>2</sup>
- Maximum particle (grit) size: Fine (< 100 µm)
- Density: Approx. 1.4 g/cm<sup>3</sup>

## Application

### Suitable Substrates

The substrate must be sound/stable, dry, clean, and free from all substances that may prevent good adhesion. In Germany: Follow VOB, part C, DIN 18 363, paragraph 3.

### Substrate Preparation

**Renders/Plasters in Mortar Groups/Classes P II (Lime-Cement Mortars) and P III (Cement Mortars):** Solid renders/plasters with normal absorbency require no preliminary treatment. Prime highly porous, sanding or absorbent renders/plasters with OptiGrund E.L.F. or CapaSol LF.

**Gypsum Mortar and Ready-Mixed Gypsum Plasters of Mortar Group/Class P IV:** Apply one priming coat of Caparol-Haftgrund. Sand sintered surfaces, remove sanding dust and apply one priming coat of Caparol-Tiefgrund TB.

**Gypsum Wallboards:** Prime absorbent boards with OptiGrund E.L.F. or Caparol-Tiefgrund TB. Prime highly compacted, smooth boards with Caparol-Haftgrund to improve bonding.

**Gypsum Plaster Boards (Sandwich Type Plaster Boards / Am.: Drywalls):** Sand off any burrs. Soft and roughened gypsum areas (repair patches) must be primed and strengthened with Caparol-Tiefgrund TB. Apply one priming coat of Caparol-Haftgrund, OptiGrund E.L.F. or CapaSol LF. Boards containing water-soluble substances that leaves marks must be primed with Caparol AquaSperrgrund. In Germany follow BFS Data Sheet No. 12.

**Concrete:** Remove all residues of releasing agents and chalking or sanding substances.

**Autoclaved Aerated Concrete (AAC) / Cellular Concrete:** Prime with a 1 : 3 mixture of Capaplex and tap (potable) water.

**Fair-Faced Brick and Sand-Lime Brick Masonry:** No preliminary treatment required.

**Sound/Stable Existing Coatings:** Treat matt, slightly absorbent coatings without a preliminary preparation. Roughen/sand glossy surfaces and enamel coatings. Apply one priming coat of Caparol-Haftgrund.

**Unsound Existing Coatings:** Remove unstable enamels and emulsion/dispersion/latex paints or synthetic resin-bound (organic) renders/plasters. Prime slightly absorbent, even surfaces with Caparol-Haftgrund. Prime highly porous, sanding or absorbent substrates with OptiGrund E.L.F. or CapaSol LF. Remove unstable coats of mineral paint by mechanical means and remove all dust. Prime with Caparol-Tiefgrund TB.

**Glue-Bound Distemper (Limewater Colour):** Wash off the existing distemper very thoroughly, allow to fully dry and prime with Caparol-Tiefgrund TB.

**Unpainted Woodchip/Ingrain, Textured or Embossed Wallpapers (made of Paper):** Coat without any preliminary treatment.

**Non-Adherent Wallpapers:** Remove completely and wash off all residues of wallpaper paste/glue and waste paper. Prime the substrate with Caparol-Tiefgrund TB.

**Mildewed Surfaces:** Remove fungal attack (fungi/mildew/mould) by wet cleaning, then use Capatox or FungiGrund and allow to dry thoroughly. Prime according to the type and condition of the substrate. Apply a finishing coat of Indeko-W, Malerit-W or Fungitex-W on badly infested surfaces in compliance with legal and official regulations (follow e.g. Ordinance on Biological Agents and Ordinance on Hazardous Substances).

**Surfaces Stained by Nicotine, Water, Soot or Fat/Grease:** Remove nicotine, soot or fat/grease stains by washing with tap water adding a grease-dissolving household detergent, then allow the substrate to dry thoroughly. Clean dried-up water stains by dry brushing. Apply an insulating coat of Caparol AquaSperrgrund. Apply one finishing coat of Aqua-inn N° 1 on highly soiled surfaces.

**Wood and Derived Timber Products:** Coat with dilutable, ecologically compatible Capacryl acrylic enamels or Capacryl PU enamels.

**Small Defects:** After having completed the necessary preparations, repair small defects with Caparol-Akkordspachtel in accordance with our application instructions, and if necessary, prime subsequently.

# TECHNICAL INFORMATION NO. 310

Method of Application	Applicable with paint brush, paint roller or airless spray equipment. <b>Airless application:</b> Spray angle: 50°; Nozzle size: 0.018" to 0.021"; Optimal spray pressure: 150 to 180 bar. Stir well and sieve the paint before application. Clean tools/ equipment immediately after use with water.
Surface Coating System	One evenly and generously applied coat of Indeko-plus, undiluted or diluted up to a max. of 5 % with tap (potable) water. High-contrast surfaces require a preliminary first coat of Indeko-plus, diluted up to max. 10 % with tap water. Prime unevenly absorbent substrates with Caparol-Haftgrund.
Consumption	Approx. 125 ml/m <sup>2</sup> per coat on an even substrate. On rough-textured surfaces correspondingly more. The exact rate of consumption is best established by a trial coating.
Application Conditions	<b>Lower Temperature Limit for Application and Drying:</b> +5 °C for product, substrate and ambient air.
Drying/Drying Time	At +20 °C and 65 % relative humidity surface-dry and recoatable after 4 - 6 hours. Completely dry and ready for stress (loadable) after approx. 3 days. Lower temperatures and higher humidity extend the drying time.
Note	To avoid lapping, the product should be applied wet-on-wet and without interruption. Due to the use of Caparol-Tiefgrund TB in the interiors, a typical solvent odour is released, hence proper ventilation must be provided during application and drying. Use non-aromatic, low-odour AmphiSilan-Putzfestiger in sensitive areas. Mechanical stress (scratching) on surfaces in dark shades may produce noticeable bright-toned stripes. For intensively coloured coatings on surfaces subjected to mechanical loads we recommend the application of an additional protective coat of PremiumColor, tinted to match the Indeko-plus coat in shade. Follow Technical Information PremiumColor. Touching up surfaces is depending on many parameters and noticeable marks of repaired areas cannot be avoided. (In Germany: See BFS Data Sheet No. 25)

## Advice

German Certificates The Fraunhofer Wilhelm-Klauditz-Institute (WKI) has audited the inoffensive application for interior use. The product is certified with German TÜV quality mark "pollutant-tested / supervised manufacturing process". German certificate is available on request.

Please Note (Status as at Date of Publication) Keep out of reach from children. Use P2 dust filter for grinding. Ensure good ventilation during use and drying. Do not eat, drink or smoke while using the paint. In case of contact with eyes or skin, immediately and thoroughly rinse with water. Do not allow product to enter drains, waterways or soil. Clean utensils immediately after use with soap and water. Do not inhale spray dust. Use dust collector A2/P2. Further information: See Material Safety Data Sheet (MSDS).

Disposal Materials and all related packaging must be disposed of in a safe way in accordance with the full requirements of the local authorities. Particular attention should be made to removing wastage from site in compliance with standard construction site procedures.  
In Germany: Dispose containers with residues of liquid product via waste collection point accepting old paints and enamels. Dispose dried/hardened product residues as construction site/demolition/municipal or domestic waste.

EU limit value for the VOC content of this product (category A/a): max. 30 g/l (2010). This product contains < 1 g/l VOC.

Product Code Paints and Enamels M-DF01

Substances of Content - Declaration Polyvinyl acetate resin dispersion, titanium dioxide, silicates, calcium carbonate, water, additives, preservative

Customer Service Centre Customer Service Center:  
Tel: 01785-818998  
E-mail: info@caparol.co.uk

## Technical Information No. 310 · Issue: June 2023

All suggestions and application instructions herein are based on our latest technical experience. Due to the wide variety of individual project conditions, we cannot be held responsible for their content. These instructions do not release the purchaser/ applicator from his responsibility to determine the suitability of the product in consideration of the project characteristics. These instructions are to be considered void when a new edition is released. Our general conditions of sale and delivery in their latest edition apply. This document is a translation of our German Technical Information No.310 · Indeko-plus · Issued: April 2022